



# FOLON.A RUBBER TECHNOLOGY CO., LTD.

TEST REPORT			2023/1/10 11:32	
MATERIAL	E70B01		LOT.NO:1126	
Original Properties		SPEC	Test Methods	Value
Shore A hardness	Points	70±5	D-2240	68
Tensile strength psi	MPa	14	D-412	15.2
Elongation	%	200	D-412	310
<b>Heat Aged,125°C@70hr</b>				
Hardness change	Points	+10	D-573	1
Tensile strength change	%	-25	D-573	-4.9
Elongation change	%	-25	D-573	-9.6
<b>Compression Set,100°C@22hrs</b>				
Compression set	%	25	D-395	17.3
<b>Compression Set,50°C@22hrs</b>				
Compression set	%	25	D-395	13.6
<b>Low Temperature -55°C@3min</b>				
Low Temperature -55°C@3min				Pass

Engineer :Yangli

Plant Manager :